

## UU E15.20 RFQ FG



Article code: FBUU054561

## General information

<b>Product group</b>	High performance flat belts
<b>Product sub type</b>	QuickSplice
<b>Industry segment</b>	Logistics
<b>Main product feature</b>	Low friction surface, Foodgrade
<b>Application</b>	Roller drives
<b>Indication of use</b>	Bi-directional

## Belt construction

<b>Tension member</b>		Polyester fabric
<b>Top side</b>	<b>material</b>	Polyurethane
	<b>finish</b>	Fine
	<b>color</b>	Royal blue
<b>Bottom / Pulley side</b>	<b>material</b>	Polyurethane
	<b>finish</b>	Rough
	<b>color</b>	Royal blue

## Characteristics

<b>Food Grade (FG)</b>	yes	According: EC 1935/2004, EU 10/2011; FDA; FDA
<b>Anti-static (AS)</b>	yes	
<b>High conductive (HC)</b>	no	

## Technical data

<b>Belt thickness</b>	according to ISO 2286-3		2 mm	0.08 in.
	tolerance	±	0.2 mm	0.01 in.
<b>Weight</b>	according to ISO 290703-1		2.2 kg/m <sup>2</sup>	0.45 lbs/ft <sup>2</sup>
<b>Force at 1% elongation</b>	according to ISO 21181	dynamic	15 N/mm	85.65 lbs/in.
<b>Recommended elongation</b>		min./max.	0.5 / 1.5 %	
<b>Coefficient of friction, dynamic</b>	according to ISO 21182	bottom side to steel	0.2	
		top side to steel	0.2	
<b>Minimum pulley diameter</b>	flexing		30 mm	1.18 in.
	back flexing		30 mm	1.18 in.
<b>Operating temperature</b>	continuous	from/to	0 / 60 °C	32 / 140 °F
<b>Belt width</b>	standard		1200 mm	47.24 in.

## Fabrication

<b>Recommended splice method</b>	QuickSplice110
<b>Alternative splice method</b>	QuickSplice50

### **Additional Information**

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F) and 65% relative humidity, unless otherwise stated, individual data may differ.

Consult our specialists for further instructions regarding joining, storage & maintenance, tracking & tensioning.

Consult our specialists for calculations with our E-RappCalc© technical calculation program.