

# UU N16 RSQ FG

Article code: FB0054540

## General information

<b>Product group</b>	High performance flat belts
<b>Product sub type</b>	QuickSplice
<b>Industry segment</b>	Food, Logistics; Paper & print
<b>Main product feature</b>	Elastic, Foodgrade
<b>Application</b>	Paper processing, Printing & finishing, Mail handling
<b>Indication of use</b>	Bi-directional

## Belt construction

<b>Tension member</b>		Polyurethane
<b>Top side</b>	<b>material</b>	Polyurethane
	<b>finish</b>	Rough
	<b>color</b>	Royal blue
<b>Bottom / Pulley side</b>	<b>material</b>	Polyurethane
	<b>finish</b>	smooth
	<b>color</b>	black

## Characteristics

<b>Food Grade (FG)</b>	yes	EC 1935/2004, EU 10/2011; FDA
<b>Antistatic (AS)</b>	yes	
<b>High conductive (HC)</b>	no	

## Technical data

<b>Belt thickness</b>	ISO 2286-3		1.1 mm	0.04 in.
<b>Weight</b>	ISO 290703-1		1.3 kg/m <sup>2</sup>	0.27 lbs/ft <sup>2</sup>
<b>Force at 6% elongation</b>	ISO 21181	dynamic	1.6 N/mm	9.14 lbs/in.
	ISO 527	static	2 N/mm	11.42 lbs/in.
<b>Recommended elongation</b>		min. / max.	0.5 / 6 %	
<b>Coefficient of friction, dynamic</b>	ISO 21182	bottom side to steel	0,2	
		top side to steel	0,2	
<b>Minimum pulley diameter</b>	flexing		20 mm	0.79 in.
	back flexing		20 mm	0.79 in.
<b>Operating temperature</b>	continuous	from / to	-10 / 60 °C	14 / 140 °F
<b>Belt width</b>	standard		1200 mm	47.24 in.

## Fabrication

<b>Recommended splice method</b>	QuickSplice30
<b>Alternative splice method</b>	OverLapSplice3

## Additional Information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.  
 Consult our specialists for further instructions regarding joining, storage & maintenance, tracking & tensioning.  
 Consult our specialists for calculations with our E-RappCalc© technical calculation program.