

COTTON 3PLY - 12

Article code: SBCO000932

General information

Product group Synthetic Belts

Belt construction

Number of plies		3
	finish	non-slip
	finish	bare fabric

Characteristics

Food Grade (FG)	no
Antistatic (AS)	no
High conductive (HC)	no
Flame-retardant (FR)	no
ATEX approval	no

Technical data

Thickness	AB method KV.002	total	3.5 mm	0.14 in.
Weight	AB method KV.004		2.725 kg/m ²	0.56 lbs/ft ²
Operating temperature	continuous	from / to	10 / 120 °C	50 / 248 °F
Manufacturing width	standard		304.8 mm	12 in.
	maximum		304.8 mm	12 in.

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive.

For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the separate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

