**Technical datasheet** 

## Flexam EX 10/2 00+05 black M2 AS FR /AMD



Article code: SBFL576361

General information							
roduct group Synthetic Belts							
Industry segment	Airports; Logistics: Distribution & warehousing						
Main product feature	Antistatic, Flame retardant, Low noise, Energy saving						
Indication of use	Flat, Rollers, Slider bed						
Belt construction							
Tension layer	polyester, stable						
Number of plies		2					
Top side	material	Flexam, PVC					
	finish	smooth, M2 Matt finish					
	color	black					
Bottom side	material	Ropanol, PUR					
	finish	impregnated fabric					
	color	transparent					
Characteristics							
Food Grade (FG)	no						
Antistatic (AS)	yes	ISO 21178					
High conductive (HC)	no	100 111/0					
Flame-retardant	yes	ISO 340					
	no						
ATEX approval	no						
Technical data							
Hardness	ISO 868		top side	80A	Shore		
Force at 1% elongation (static)	ISO 21181			10	N/mm	57.1	lbs/in.
Elastic modulus (k1% relaxed)	ISO 21181			6.5	N/mm	37.12	lbs/in.
Thickness	AB method KV.002		total	2.20	mm	0.09	in.
			top cover	0.50	mm	0.02	in.
Weight	AB method KV.004			2.6	kg/m²	0.53	lbs/ft <sup>2</sup>
Coefficient of friction	bottom against steel top against steel		dynamic	0.17			
			static	0.2			
			dynamic	0.4			
			static	0.5			
Operating temperature	continuous short		from / to	-15 / 80	°C	5 / 176	°F
			from / to	-15 / 100		5 / 212	
Minimum pulley diameter	flexing			60	mm	2.36	
	backflexing			80	mm	3.15	in.
Manufacturing width	standard			2020		79.53	
-	maximum			2020		79.53	

## Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

## Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.