**Technical datasheet** 

## PHB M 135/3 BBxBB black FR

Article code: RBPH000016



General information		
Productgroup	Rubber Belts	
Industry segment	Logistics: Distribution & warehousing	
Main product feature	Flame retardant	
Indication of use	Slider bed, Rollers	

Belt construction		
Tension layer		polyester/polyamide
Lateral stability		yes, exeptionally laterally stiff
Number of plies		3
Top side	material	impregnated fabric
	color	black
Bottom side	material	impregnated fabric
	color	black

Characteristics		
Antistatic (AS)	no	
Flame-retardant (FR)	yes	ASTM D-378

Technical data						
Elastic modulus (k1% relaxed)	ISO 21181		12	N/mm	68.52	lbs/in.
Rated working tension			24	N/mm	137.04	lbs/in.
Elongation at rated tension			2	%		
Longitudinal tear			445	N	100.04	Lb
Finished belt gauge			4	mm	0.16	in.
Belt weight			5.5	kg/m²	1.13	lbs/ft²
Coefficient of friction	bottom against steel	dynamic	0.2			
		static	0.25			
	top against steel	dynamic	0.2			
		static	0.25			
Operating temperature	continuous	from / to	-20 / 80	°C	-4 / 176	°F
	short	from / to	-20 / 90	°C	-4 / 194	°F
Minimum pulley diameter	flexing		119.4	mm	4.7	in.
Manufacturing width	maximum		1829	mm	72.01	in.

Fabrication	
Corrugated side walls	no
Profiles on top side	yes
Profiles on bottom side	yes
Mechanical fasteners	Clipper # 3 HT

## Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to pretension the belt to a level that it does not slip at full belt load.

During the life time of the belt, the pretension should not go below this level.

To maximize the service life of the belt we recommend not to increase the belt tension above this level.