Technical datasheet

## Butyl EP 12/2 00+C37 black CR HR

Article code: LWBU560414



| General information  |                                     |
|----------------------|-------------------------------------|
| Product group        | Light Weight Rubber                 |
| Main product feature | Cold resistant, Heat resistant      |
| Indication of use    | Flat, Rollers, Troughed, Slider bed |

| Belt construction |          |                                |
|-------------------|----------|--------------------------------|
| Tension layer     |          | RFL polyester/nylon, flexible  |
| Number of plies   |          | 2                              |
| Top side          | material | Butyl, BU                      |
|                   | finish   | profile, C37 Supergrip profile |
|                   | color    | black                          |
| Bottom side       | material | fabric, polyester/nylon        |
|                   | finish   | impregnated                    |
|                   | color    | red                            |

| Characteristics |    |  |
|-----------------|----|--|
| Food Grade (FG) | no |  |

| Technical data         |                  |           |           |       |             |         |
|------------------------|------------------|-----------|-----------|-------|-------------|---------|
| Hardness               | ISO 868          | top side  | 50A       | Shore |             |         |
| Force at 1% elongation | ISO 21181        |           | 12        | N/mm  | 68.52       | lbs/in. |
| Thickness              | AB method KV.002 | belt      | 7.3       | mm    | 0.29        | in.     |
|                        |                  | top cover | 3.8       | mm    | 0.15        | in.     |
| Weight                 | AB method KV.004 |           | 5.6       | kg/m² | 1.15        | lbs/ft² |
| Operating temperature  | continuous       | from / to | -40 / 149 | °C    | -40 / 300.2 | °F      |
|                        | short            | from / to | -40 / 149 | °C    | -40 / 300.2 | °F      |
| Manufacturing width    | standard         |           | 1829      | mm    | 72.01       | in.     |
|                        | maximum          |           | 1829      | mm    | 72.01       | in.     |

## **Fabrication**

Vulcanizing is always preferable. Cold splicing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

## **Additional information**

This sheet contains typical values, which apply to a temperature of approx. 20  $^{\circ}$ C (68  $^{\circ}$ F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.