Technical datasheet

General information

Ropanyl ESM 5/2 00+015 white AS FG NF

Article code: SBRY576410



0.15 mm

-20 / 90 °C

-30 / 110 °C

1.4 kg/m²

5 mm

20 mm

1900 mm

1900 mm

154 W/(m².K)

0.01 in.

-4/194 °F

-22 / 230 °F

0.2 in.

0.79 in.

74.8 in.

74.8 in.

0.29 lbs/ft²

27.14 BTU/(h.ft².°F)

General Information							
Product group	Synthetic Belts	Synthetic Belts					
Industry segment	Food: Confectionary & candy, Bakery						
Main product feature	Antistatic, Foodgrade, Non-fraying, Knife edge transfer						
Indication of use	Slider bed, Rollers, Fl	Slider bed, Rollers, Flat, Troughed					
Belt construction							
Tension layer		polyester, stable	2				
Number of plies		2	2				
Top side	material	Ropanyl, TPU	Ropanyl, TPU				
	finish	smooth, glossy	smooth, glossy				
	color	white	white				
Bottom side	material	Ropanol, PUR	Ropanol, PUR				
	finish	impregnated fab	impregnated fabric, PUR				
	color	white	white				
Characteristics							
Food Grade (FG)	yes	EC 1935/2004, EU 10/2011; FDA					
Antistatic (AS)	yes	ISO 21178					
High conductive (HC)	no						
Flame-retardant (FR)	no						
ATEX approval	no						
Technical data							
Hardness	ISO 868	top side	85A Shore				
Force at 1% elongation (static)	ISO 21181		5 N/mm	28.55 lbs/in.			
Thickness	AB method KV.002	total	1.30 mm	0.05 in.			

top cover

from / to

from / to

	Fa	hr	ica	tic	'n
--	----	----	-----	-----	----

Weight

Heat transfer coefficient

Minimum pulley diameter

Manufacturing width

Operating temperature

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

AB method KV.004

continuous

backflexing

standard

maximum

short

flexing

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.