Technical datasheet

GG E05.14 FFQ



Article code: FBGG054607

General information	
Product group	High performance flat belts
Product sub type	QuickSplice
Industry segment	Postal automation; Paper & print
Main product feature	Abrasion resistant, High grip
Application	Mail handling, Paper processing, Printing & finishing
Indication of use	Bi-directional, High efficient rubber cover
Belt construction	

Tension member		Polyester fabric
Top side	material	XNBR elastomer
	finish	Fine
	color	green
Bottom / Pulley side	material	XNBR elastomer
	finish	Fine
	color	black

Characteristics		
Food Grade (FG)	no	
Antistatic (AS)	yes	
High conductive (HC)	no	

Technical data						
Belt thickness	ISO 2286-3		1.4	mm	0.06	in.
Weight	ISO 290703-1		1.5	kg/m²	0.31	lbs/ft²
Force at 1% elongation	ISO 21181	dynamic	5	N/mm	28.55	lbs/in.
	ISO 527	static	6.9	N/mm	39.4	lbs/in.
Recommended elongation		min. / max.	0.5 / 2	%		
Coefficient of friction, dynamic	ISO 21182	bottom side to steel	0,5			
		top side to steel	0,5			
Minimum pulley diameter	flexing		25	mm	0.98	in.
	back flexing		25	mm	0.98	in.
Operating temperature	continuous	from / to	0 / 60	°C	32 / 140	°F
Belt width	standard		570	mm	22.44	in.
Fabrication						

Recommended splice method

Additional Information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. Consult our specialists for further instructions regarding joining, storage & maintenance, tracking & tensioning. Consult our specialists for calculations with our E-RappCalc© technical calculation program.

QuickSplice50

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.