**Technical datasheet** 

## **GG N15 FFQ HC**

Article code: FBGG054585



General information			
Product group	High performance flat belts		
Product sub type	QuickSplice		
Industry segment	Paper & print; Postal automation		
Main product feature	Elastic, High conductivity		
Application	Paper processing, Printing & finishing, Mail handling		
Indication of use	Bi-directional, High efficient rubber cover		

Belt construction		
Tension member		Thermoplastic elastomer
Top side	material	XNBR elastomer
	finish	Fine
	color	black
Bottom / Pulley side	material	XNBR elastomer
	finish	Fine
	color	black

Characteristics				
Food Grade (FG)	no			
Antistatic (AS)	yes	ISO 284		
High conductive (HC)	yes	ISO 284		
ATEX approval	no			

Technical data						
Belt thickness	DIN EN ISO 2286-3		1.4	mm	0.06	in.
	tolerance	±	0.1	mm	0	in.
Weight	ISO 290703-1		1.4	kg/m²	0.29	lbs/ft²
Force at 6% elongation	DIN EN ISO 21181	dynamic	1.5	N/mm	8.57	lbs/in.
	DIN EN ISO 527	static	1.4	N/mm	7.99	lbs/in.
Recommended elongation		min. / max.	0.5 / 6	%		
Coefficient of friction, dynamic	DIN EN ISO 21182	bottom side to steel	0,5	μ		
		top side to steel	0,5	μ		
Minimum pulley diameter	flexing		15	mm	0.59	in.
	back flexing		15	mm	0.59	in.
Operating temperature	continuous	from / to	0 / 60	°C	32 / 140	°F
Belt width	standard		780	mm	30.71	in.

Fabrication			
QuickSplice30			
ButtSplice75			

## **Additional Information**

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

Consult our specialists for further instructions regarding joining, storage & maintenance, tracking & tensioning.

Consult our specialists for calculations with our E-RappCalc© technical calculation program.

Our material, as well as the packaging, must be disposed of in a professional and environmentally friendly manner.

This item contain the following substance included on the candidate list according to article 59 (1, 10) of Regulation (EC) No 1907/2006 "REACH" in a concentration above 0.1 % weight by weight: 6,6'-di-tert-butyl-2,2'-methylenedi-p-cresol [119-47-1]