**Technical datasheet** 

## **GG N15 FFQ HC**

Article code: FBGG054585



General information	
Product group	High performance flat belts
Product sub type	QuickSplice
Industry segment	Paper & print; Postal automation
Main product feature	Elastic, High conductivity
Application	Paper processing, Printing & finishing, Mail handling
Indication of use	Bi-directional, High efficient rubber cover

Belt construction				
Tension member		Thermoplastic elastomer		
Top side	material	XNBR elastomer		
	finish	Fine		
	color	black		
Bottom / Pulley side	material	XNBR elastomer		
	finish	Fine		
	color	black		

Characteristics		
Food Grade (FG)	no	
Antistatic (AS)	yes	ISO 284
High conductive (HC)	yes	ISO 284
ATEX approval	no	

Technical data						
Belt thickness	DIN EN ISO 2286-3		1.4	mm	0.06	in.
	tolerance	±	0.1	mm	0	in.
Weight	ISO 290703-1		1.4	kg/m²	0.29	lbs/ft²
Force at 6% elongation	DIN EN ISO 21181	dynamic	1.5	N/mm	8.57	lbs/in.
	DIN EN ISO 527	static	1.4	N/mm	7.99	lbs/in.
Recommended elongation		min. / max.	0.5 / 6	%		
Coefficient of friction, dynamic	DIN EN ISO 21182	bottom side to steel	0,5	μ		
		top side to steel	0,5	μ		
Minimum pulley diameter	flexing		15	mm	0.59	in.
	back flexing		15	mm	0.59	in.
Operating temperature	continuous	from / to	0 / 60	°C	32 / 140	°F
Belt width	standard		780	mm	30.71	in.

## **Fabrication**

QuickSplice30

ButtSplice75

## **Additional Information**

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

Consult our specialists for further instructions regarding joining, storage & maintenance, tracking & tensioning.

Consult our specialists for calculations with our E-RappCalc© technical calculation program.

Our material, as well as the packaging, must be disposed of in a professional and environmentally friendly manner.

This item contain the following substance included on the candidate list according to article 59 (1, 10) of Regulation (EC) No 1907/2006 "REACH" in a concentration above 0.1 % weight by weight: 6,6'-di-tert-butyl-2,2'-methylenedi-p-cresol [119-47-1]

Because of continuous development, the presented data is subject to alteration. This data replaces that included in previous publications. Ammeraal Beltech excludes any liability for the incorrect use of the above stated information. Subject to the general terms and conditions of sale and delivery, as applied by its operating companies, are all activities performed and services rendered by Ammeraal Beltech.