Technical datasheet

Excon EF 30/3 07+20 dark green AS FR FG

Ammeraal Beltech
Innovation & Service in Belting

Article code: SBMD000075

General information	
Product group	Synthetic Belts
Industry segment	General industry
Main product feature	Antistatic, Flame retardant, Abrasion resistant, Oil & grease resistant
Indication of use	Flat, Rollers, Troughed

Belt construction		
Tension layer		polyester, flexible
Number of plies		3
Top side	material	PVCEXCON, PVC
	finish	smooth, glossy
	color	dark green
Bottom side	material	PVCEXCON, PVC
	finish	smooth, glossy
	color	dark green

Characteristics		
Food Grade (FG)	yes	EC 1935/2004, EU 10/2011; FDA
Antistatic (AS)	yes	ISO 21178
Flame-retardant (FR)	yes	ISO 340
ATEX approval	2	

Technical data						
Hardness	ISO 868	top side	75A	Shore		
Force at 1% elongation (static)	ISO 21181		30	N/mm	171.3	lbs/in.
Thickness	AB method KV.002	total	6.20	mm	0.24	in.
		top cover	2.00	mm	0.08	in.
Weight	AB method KV.004		7.5	kg/m²	1.54	lbs/ft²
Operating temperature	continuous	from / to	-10 / 70	°C	14 / 158	°F
	short	from / to	-15 / 80	°C	5 / 176	°F
Minimum pulley diameter	flexing		250	mm	9.84	in.
	backflexing		300	mm	11.81	in.
Manufacturing width	standard		2400	mm	94.49	in.
	maximum		2400	mm	94.49	in.

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.