

Flexam EM 15/3 0+A79 grey

Article code: SBFL574752

General information

Product group	Synthetic Belts
Industry segment	Wood
Main product feature	High grip
Indication of use	Slider bed, Rollers, Flat

Belt construction

Tension layer		polyester, stable
Number of plies		3
Top side	material	Flexam, PVC
	finish	profile, A79 Diamond profile 19 mm
	color	grey
Bottom side	material	fabric, polyester
	finish	bare fabric
	color	natural

Characteristics

Food Grade (FG)	no	
Antistatic (AS)	no	
High conductive (HC)	no	
ATEX approval	yes	ATEX III

Technical data

Hardness	ISO 868	top side	55A Shore	
Force at 1% elongation (static)	ISO 21181		15 N/mm	85.65 lbs/in.
Thickness	AB method KV.002	total	7.8 mm	0.31 in.
		top cover	4.8 mm	0.19 in.
Weight	AB method KV.004		6.1 kg/m ²	1.25 lbs/ft ²
Coefficient of friction	bottom against steel	dynamic	0.19	
		static	0.22	
	top against steel	dynamic	> 1.0	
		static	> 1.5	
Operating temperature	continuous	from / to	-15 / 80 °C	5 / 176 °F
	short	from / to	-15 / 100 °C	5 / 212 °F
Minimum pulley diameter	flexing		120 mm	4.72 in.
	backflexing		220 mm	8.66 in.
Manufacturing width	standard		1350 mm	53.15 in.
	maximum		2010 mm	79.13 in.

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive.

For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the separate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.