Technical datasheet

Flexam EF 70/4 00+R6 Dark green

Article code: SBMD000118



Technical data						
Hardness	ISO 868	top side	74A	Shore		
Force at 1% elongation (static)	ISO 21181		70	N/mm	399.71	lbs/in.
Thickness	AB method KV.002	total	9.00	mm	0.35	in.
		top cover	2.45	mm	0.1	in.
Weight	AB method KV.004		10.8	kg/m²	2.21	lbs/ft²
Operating temperature	continuous	from / to	-10 / 70	°C	14 / 158	°F
	short	from / to	-10 / 70	°C	14 / 158	°F
Minimum pulley diameter	flexing		450	mm	17.72	in.
	backflexing		500	mm	19.69	in.
Manufacturing width	standard		2400	mm	94.49	in.

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the separate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts. Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.

Ammeraal Beltech

Innovation & Service in Rel