

Nitrile ES 8/2 01+C46 white FG

Article code: LWNIS60007

General information

| | |
|-----------------------------|---|
| Product group | Light Weight Rubber |
| Industry segment | Food: Fish & seafood, Fruit & vegetable, Bakery |
| Main product feature | Foodgrade |
| Indication of use | Slider bed, Rollers, In/declined conveying |

Belt construction

| | | |
|------------------------|-----------------|----------------------------------|
| Tension layer | | polyester spun, flexible |
| Number of plies | | 2 |
| Top side | material | Nitrile, Nitrile |
| | finish | profile, C46 Pyramid top profile |
| | color | white |
| Bottom side | material | Nitrile, polyester |
| | finish | smooth |
| | color | white |

Characteristics

| | | |
|------------------------|-----|-----------|
| Food Grade (FG) | yes | FDA; USDA |
|------------------------|-----|-----------|

Technical data

| | | | | |
|-------------------------------|------------------|-----------|-----------------------|--------------------------|
| Hardness | ISO 868 | top side | 62A Shore | |
| Force at 1% elongation | ISO 21181 | | 8 N/mm | 45.68 lbs/in. |
| Thickness | AB method KV.002 | belt | 3.5 mm | 0.14 in. |
| | | top cover | 2.2 mm | 0.09 in. |
| Weight | AB method KV.004 | | 3.2 kg/m ² | 0.66 lbs/ft ² |
| Operating temperature | continuous | from / to | -18 / 121 °C | -0.4 / 249.8 °F |
| | short | from / to | -18 / 121 °C | -0.4 / 249.8 °F |
| Manufacturing width | standard | | 1524 mm | 60 in. |
| | maximum | | 1742.4 mm | 68.6 in. |

Fabrication

Vulcanizing is always preferable. Cold splicing can only be done when the belt is exposed to normal temperature and the humidity is not excessive.

For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the separate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.