Flexam EM 8/2 00+04 light blue AS FG



Article code: SBFL573000

General information	
Product group	Synthetic Belts
Industry segment	Food: Fruit & vegetable; Container & packaging
Main product feature	Antistatic, Foodgrade
Indication of use	Slider bed, Rollers, Flat

Belt construction		
Tension layer		polyester, stable
Number of plies		2
Top side	material	Flexam, PVC
	finish	smooth, glossy
	color	Light blue
Bottom side	material	Ropanol, PUR
	finish	impregnated fabric
	color	transparent

Characteristics						
Food Grade (FG)	yes	EC 1935/2004, EU 10/2011; FDA				
Antistatic (AS)	yes	ISO 21178				
High conductive (HC)	no					
ATEX approval	no					

Technical data									
Hardness	ISO 868	top side	80A	Shore					
Force at 1% elongation (static)	ISO 21181		8	N/mm	45.68	lbs/in.			
Thickness	AB method KV.002	total	1.80	mm	0.07	in.			
		top cover	0.40	mm	0.02	in.			
Weight	AB method KV.004		2.1	kg/m²	0.43	lbs/ft²			
Operating temperature	continuous	from / to	-15 / 80	°C	5 / 176	°F			
	short	from / to	-15 / 100	°C	5 / 212	°F			
Minimum pulley diameter	flexing		25	mm	0.98	in.			
	backflexing		50	mm	1.97	in.			
Manufacturing width	standard		2000	mm	78.74	in.			
	maximum		2000	mm	78.74	in.			

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the seperate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 $^{\circ}$ C (68 $^{\circ}$ F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.