

## Felt NPF 40 black HC

Article code: SBFE000045

### General information

<b>Product group</b>	Synthetic Belts
<b>Main product feature</b>	High conductivity

### Belt construction

<b>Number of plies</b>		1
<b>Top side</b>	<b>material</b>	felt, FE
	<b>color</b>	black
<b>Bottom side</b>	<b>material</b>	felt
	<b>finish</b>	felt
	<b>color</b>	black

### Characteristics

<b>Food Grade (FG)</b>	no	
<b>Antistatic (AS)</b>	no	
<b>High conductive (HC)</b>	yes	ISO 284
<b>Flame-retardant (FR)</b>	no	
<b>ATEX approval</b>	no	

### Technical data

<b>Thickness</b>	AB method KV.002	total	3.90 mm	0.15 in.
<b>Weight</b>	AB method KV.004		2 kg/m <sup>2</sup>	0.41 lbs/ft <sup>2</sup>
<b>Coefficient of friction</b>	bottom against steel	dynamic	0.22	
		static	0.26	
	top against steel	dynamic	0.22	
		static	0.26	
<b>Operating temperature</b>	continuous	from / to	-20 / 120 °C	-4 / 248 °F
	short	from / to	-20 / 120 °C	-4 / 248 °F
<b>Minimum pulley diameter</b>	flexing		70 mm	2.76 in.
	backflexing		140 mm	5.51 in.
<b>Manufacturing width</b>	standard		2000 mm	78.74 in.
	maximum		2000 mm	78.74 in.

### Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive.

For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the separate information.

### Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ.

We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts.

Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging.

For details consult 'Storage and handling instructions' or contact our specialist.